

A03/25/51

TELEGRAPH OFFICE
COMPTON,
SURREY.

LIMNERSLEASE,
GUILDFORD,
(3 MILES)

Sesso Marico

Put 1 lb plaster of Paris
into a pail full of water
stirring with a stick as
you drop it in, stir well,
let it settle & pour off
the water adding fresh,
stir again & repeat the
process for a week, stirring
two or three times a day,
after this once is sufficient
as the plaster will no
longer cake. This must be

done for a month, then
pour off the water, &
make up the plaster into
small batches about the
size of a very small roll
& let them dry in the air.
They should be kept in an
airy place out of wet
but with a free current
round. they used to have
lofts with wooden shutters,
such as the french houses
have to keep off the sun.
When required for use
take off the required

quantity & stand it in
water till it has taken
up as much as it will
hold & scrape it with a
knife into the size or
milk (skimmed) if for
priming.

This can be used for gilding
& working in relief.